DMEGC SOLAR

TIER 1 Bloomberg NEW ENERGY FINANCE

iNFINITY RT 3.0


N-type

Mono facial Module with Double Glass

DMxxxG12RT-G54HBB

510~535W

23.9%
Max. Efficiency




Please refer to the DMEGC Standard Limited Warranty for more details about the product warranty and power warranty.

Outstanding Aesthetics
Designed with aesthetics in mind and manufactured using DMEGC Advanced Black Technology.

Extended Stress Tests
Protection against harsh environmental conditions Certified by TÜV.

Leading Manufacturing
40+ years experience in high-tech manufacturing.

POWER WARRANTY



≤1% 1st-year Degradation, ≤0.35% Linear Annual Degradation (2nd to 30th year)

COMPANY MANAGEMENT SYSTEM

SA 8000: ILO Standards. Social responsibility standards
ISO 9001: Quality management system
ISO 14001: Environmental management system
ISO 45001: Occupational health and safety management system
ISO 50001: Energy management system
ISO 27001: Information security management system

PRODUCT CERTIFICATION

IEC 61215, IEC 61730
Ammonia Corrosion (IEC 62716)
Salt Mist Corrosion (IEC 61701)
LeTID (IEC TS 63342)
Dust & Sand (IEC 60068)

SolarPower Europe


Warranty partner
Munich RE

A member of Hengdian Group

DMxxxG12RT-G54HBB

Module Specification

Cell Type	N type Mono-crystalline, 108 (6×18)
Dimensions (mm)	1977×1134×30
Weight (kg)	27.1
Front Cover	2 mm heat strengthened glass, Anti-reflective coating
Rear Cover	2 mm heat strengthened glass
Junction Box	3 Diodes, IP68 according to IEC 62790
Output Cables (Including Connector)	4 mm²/Portrait: 300 mm (+) /200 mm (-) Landscape: 1200 mm (+) /1200 mm (-) Length can be customized
Connector Type	PV-D01 or MC4-EVO 2A (1500V)



Electrical Specifications[1]

Module Type	DM510G12RT-G54HBB		DM515G12RT-G54HBB		DM520G12RT-G54HBB		DM525G12RT-G54HBB		DM530G12RT-G54HBB		DM535G12RT-G54HBB	
Testing Condition	STC[2]	NMOT[3]	STC	NMOT	STC	NMOT	STC	NMOT	STC	NMOT	STC	NMOT
Maximum Power (Pmax/W)	510	389	515	392	520	396	525	400	530	404	535	408
Maximum Power Current (Imp/A)	14.96	12.16	15.03	12.21	15.10	12.27	15.17	12.33	15.24	12.38	15.31	12.44
Maximum Power Voltage (Vmp/V)	34.10	32.00	34.28	32.16	34.45	32.32	34.62	32.48	34.79	32.64	34.96	32.80
Short-circuit Current (Isc/A)	15.64	12.61	15.69	12.65	15.74	12.69	15.79	12.73	15.84	12.77	15.89	12.81
Open-circuit Voltage (Voc/V)	40.02	38.52	40.24	38.73	40.46	38.94	40.68	39.15	40.90	39.36	41.12	39.57
Module Efficiency STC (%)	22.7		23.0		23.2		23.4		23.6		23.9	

[1] Measurements according to IEC 60904-3, Measurement tolerance: Pmax: ±3%, Isc: ±4%, Voc: ±3%

[2] STC (Standard Test Condition): Radiation 1000 W/m², Module temperature 25°C, AM = 1.5

[3] NMOT: Radiation 800 W/m², Ambient temperature 20°C, AM = 1.5, Wind Speed 1 m/s

Operating Conditions

Operating Temperature (°C)	-40 to +85
Maximum System Voltage (V)	1500 DC(IEC)
Overcurrent Protection Rating (A)	30
Power Sorting (%)	0~3
Protection Class	Class II
Fire Class	Class C (IEC)
Max. Test Load, Push/Pull (Pa)	Front 5400 / Back 2400
Max. Design Load, Push/Pull (Pa)	Front 3600 / Back 1600
Hail Class	HW3*


* Reference diameter of ice balls-VKF 30mm, Ice ball storage temp -20°C.

Packaging

Container	40HQ
Pallet Dimensions (mm)	1985x1140x1250
Pieces per Pallet	36
Pieces per Container	864

Temperature Characteristics

Nominal Module Operating Temperature (NMOT)	42±2°C
Temperature Coefficient of Pmax (%/°C)	-0.29
Temperature Coefficient of Voc (%/°C)	-0.25
Temperature Coefficient of Isc (%/°C)	+0.048



Hengdian Group DMEGC Magnetics Co.,Ltd.
Add: Hengdian Industrial Zone, Dongyang City Zhejiang Province, China 322118
Tel: 0086-579-8658-8826 **E-mail:** solar@dmegc.com.cn **Website:** www.dmegcsolar.com

DMEGC Renewable Energy B.V.
Add: Industrieweg 2,2641 RM Pijnacker, The Netherlands.
Tel: +31 (0) 8 58200765 **E-mail:** contact@dmegc.eu

Statement: The installation instructions and the warranty conditions must be followed. Due to technological progress, product parameters will be adjusted accordingly. When signing the contract, the latest data of the company shall prevail. All information in this data sheet corresponds to EN 50380.Changes and errors excepted. Document: EN DS-G12RT-G54HBB-20261015.
©DMEGC – All Rights Reserved